



Intertek Testing Services

Labtest

Hong Kong Government Recognized Service Supplier
Approved Laboratory of International Wool Secretariat

Members of:
American National Standards Institute
American Society for Testing and Materials
British Standards Institute

Hong Kong Association of Certification Laboratories
Hong Kong Toys Council

TEST REPORT

NUMBER: TXT409350

DATE: APR 16, 2001

APPLICANT: TUNG KONG NON-WOVEN FABRIC

MANUFACTURES LTD
RM 3D 3/F LOYAL CTR
828 CHEUNG SHA WAN RD KLN
HK

ATTN: ALBERT YU

SAMPLE DESCRIPTION:

TWO (2) PIECES OF SUBMITTED WOVEN PILLOW IN KHAKI SANDWICHED WITH
(A) PEARL FILLER AND (B) DOWN.

DATE RECEIVED/DATE TEST STARTED : APR 10, 2001.

CONCLUSION:

APPEARANCE AFTER WASH

(A) (B)

M M

NOTE : M = COMMERCIALY ACCEPTABLE

F = FAIL

= NO COMMENT

PREPARED AND CHECKED BY:
FOR INTERTEK TESTING SERVICES HK LTD

ERIC S.K. SIT
GENERAL MANAGER
TEXTILE AND FOOTWEAR DIVISION

YMTONG / tewchak

PAGE 1 OF 3

Intertek Testing Services Hong Kong Ltd.

2/F., Garment Centre, 576 Castle Peak Road, Kowloon, Hong Kong.

Tel: (852) 2173 8888 Fax: (852) 2786 1903

Attention is drawn to the terms and conditions printed overleaf.

R-LBT-O/1



Intertek Testing Services

Labtest

Hong Kong Government Recognized Service Supplier
Approved Laboratory of International Wool Secretariat

Members of:
American National Standards Institute
American Society for Testing and Materials
British Standards Institute

Hong Kong Association of Certification Laboratories
Hong Kong Toys Council

TEST REPORT

NUMBER: TXT409350

TESTS CONDUCTED (AS REQUESTED BY THE APPLICANT)

- 1 APPEARANCE AFTER WASH (12 MINUTES MACHINE WASH AT 105F, NORMAL CYCLE, IN AATCC 1993 DETERGENT SOLUTION AND FOLLOWED BY TUMBLE DRY - COTTON/STURDY) :

SAMPLE (A)

AFTER THE 1-ST WASH

OBSERVATION :

- . NO PEARL FILLER FIBRE WAS FOUND PENETRATING THROUGH THE WOVEN FABRIC.
 - . A FEW PEARL FILLER FIBRE WERE FOUND PENETRATING THROUGH THE STITCHING OF WOVEN FABRIC.
 - . TINY CREASES WERE FOUND ON THE WOVEN FABRIC.
 - . MODERATE PUCKERS WERE FOUND ALONG THE STITCHINGS.
- THE GENERAL APPEARANCE OF THE WASHED SAMPLE WAS STILL ACCEPTABLE.

AFTER THE 3-RD WASH

OBSERVATION :

- . NO PEARL FILLER FIBRE WAS FOUND PENETRATING THROUGH THE WOVEN FABRIC.
 - . A FEW PEARL FILLER FIBRE WERE FOUND PENETRATING THROUGH THE STITCHING OF WOVEN FABRIC.
 - . THE WASHED SAMPLE FADED SLIGHTLY.
 - . TINY CREASES WERE FOUND ON THE WOVEN FABRIC.
 - . MODERATE PUCKERS WERE FOUND ALONG THE STITCHINGS.
- THE GENERAL APPEARANCE OF THE WASHED SAMPLE WAS STILL ACCEPTABLE.

SAMPLE (B)

AFTER THE 1-ST WASH

OBSERVATION :

- . NO DOWN FIBRE WAS FOUND PENETRATING THROUGH THE WOVEN FABRIC.
 - . A FEW D OWN FIBRE WERE FOUND PENETRATING THROUGH THE STITCHING OF WOVEN FABRIC.
 - . TINY CREASES WERE FOUND ON THE WOVEN FABRIC.
 - . MODERATE PUCKERS WERE FOUND ALONG THE STITCHINGS.
- THE GENERAL APPEARANCE OF THE WASHED SAMPLE WAS STILL ACCEPTABLE.



Intertek Testing Services

Labtest

Hong Kong Government Recognized Service Supplier
Approved Laboratory of International Wool Secretariat

Members of:
American National Standards Institute
American Society for Testing and Materials
British Standards Institute

Hong Kong Association of Certification Laboratories
Hong Kong Toys Council

TEST REPORT

NUMBER: TXT409350

TESTS CONDUCTED (AS REQUESTED BY THE APPLICANT)

APPEARANCE AFTER WASH (CONT'D)

AFTER THE 3-RD WASH

OBSERVATION :

- NO DOWN FIBRE WAS FOUND PENETRATING THROUGH THE WOVEN FABRIC.
 - A FEW DOWN FIBRE WERE FOUND PENETRATING THROUGH THE STITCHING OF WOVEN FABRIC.
 - THE WASHED SAMPLE FADED SLIGHTLY.
 - TINY CREASES WERE FOUND ON THE WOVEN FABRIC.
 - MODERATE PUCKERS WERE FOUND ALONG THE STITCHINGS.
- THE GENERAL APPEARANCE OF THE WASHED SAMPLE WAS STILL ACCEPTABLE.
-