

Hong Kong Government Recognized Service Supplier Approved Laboratory of The Woolmark Company

Members of : American National Standards Institute American Society for Testing and Materials British Standards Institute Hong Kong Association of Certification Laboratories Hong Kong Toys Council

TEST REPORT

Number: TJ01231795

Date: Dec 03, 2005

Applicant:

TUNG KONG NON-WOVEN FABRIC

MANUFACTURES LTD RM 3D 3/F LOYAL CTR

828 CHEUNG SHA WAN RD KLN

HK

Attn: MS CHEUNG

Sample Description :

Three (3) pieces of submitted sample said to be Woven fabric quilted with padding in Lt. Green marked as (A), (B) and (C) Control sample.

Applicant's Provided Care Instruction/Label:

Hand Wash 30°C

Machine Wash And Tumble Dry

Date Received/Date Test Started: Nov 29, 2005

Order No.

9 37

Style No.

( Z

Buyer's Name

: =

Manufacturer's Name :

57 John

Ref.

: # TK-D.HC

Padding Test

Conclusion:

(A) (B)

Appearance After Wash

Appearance After Commercial Drycleaning

M1

F = Fail

- M

# = No Comment

Note : M = Commercially Acceptable

N/A = Not Applicable

Remark :

M1 Sample A is commercially acceptable in Appearance After Wash with touch up warm ironing.

For and on behalf of

Intertek Testing Services Hong Kong Limited

Eric S.K. Sit

General Manager

Textile And Footwear Division

Page 1 Of 2



Hong Kong Government Recognized Service Supplier Approved Laboratory of The Woolmark Company

American National Standards Institute American Society for Testing and Materials British Standards Institute

Hong Kong Association of Certification Laboratories Hong Kong Toys Council

TEST REPORT

Number: TJ01231795

Tests Conducted (As Requested By The Applicant)

Appearance After Wash (ISO 6330-1984, Wascator Washing Machine-Front-Loading Horizontal Rotating Drum Type, Test Programme 6A, 40°C With 2 kg Load, In 0.08% ECE Reference Detergent And 0.02% Sodium Perborate Solution, Followed By Line Dry):

(A)

## After One Wash

## Observation :

. Slight fading on washed sample.

- . A few padding fibres penetrating through washed sample and its stitching.
- The following could be improved by touch up warm ironing :
  - -Moderate puckers along stitching of shell

-Tiny creases on shell

General Appearance : Acceptable With Touch Up Warm Ironing.

Appearance After Commercial Drycleaning In Perchloroethylene:

(B)

## After One Dryclean

## Observation:

- . A few padding fibres penetrating through drycleaned sample and its stitching.
- Slight fading on drycleaned sample.

General Appearance : Acceptable

Page 2 Of