



Intertek Testing Services

Labtest

Hong Kong Government Recognized Service Supplier
Approved Laboratory of International Wool Secretariat

Members of:

American National Standards Institute
American Society for Testing and Materials
British Standards Institute

Hong Kong Association of Certification Laboratories
Hong Kong Toys Council

TEST REPORT

NUMBER: TJ00004407

APPLICANT: TUNG KONG NON-WOVEN FABRIC
MANUFACTURES LTD
RM 3D 3/F LOYAL CTR
828 CHEUNG SHA WAN RD KLN
HK

DATE: MAR 06, 2002

ATTN: MR. FONG/MS. LEUNG

SAMPLE DESCRIPTION :

ONE (1) PIECE OF SUBMITTED SAMPLE SAID TO BE 100% POLYESTER WOVEN PILLOW,
SANDWICH WITH PADDING IN NAVY.

APPLICANT'S PROVIDED CARE INSTRUCTION :

MACHINE WASH & TUMBLE DRY

DATE RECEIVED/DATE TEST STARTED : MAR 02, 2002.

ORDER NO. : -

STYLE NO. : -

BUYER'S NAME : -

MANUFACTURER'S NAME : -

REF. : 100 GM DOWN TOUCH HEAT SEAL BOTH SIDE

CONCLUSION:

APPEARANCE AFTER WASH


M

NOTE : M = COMMERCIALY ACCEPTABLE

F = FAIL

= NO COMMENT

PREPARED AND CHECKED BY:
FOR INTERTEK TESTING SERVICES HK LTD


ERIC S.K. SIT
GENERAL MANAGER
TEXTILE AND FOOTWEAR DIVISION

CPMOK / mikho

PAGE 1 OF 2

Intertek Testing Services Hong Kong Ltd.

2/F., Garment Centre, 576 Castle Peak Road, Kowloon, Hong Kong.
Tel: (852) 2173 8888 Fax: (852) 2786 1903

Attention is drawn to the terms and conditions printed overleaf.

R-LBT-O/1



Intertek Testing Services

Labtest

Hong Kong Government Recognized Service Supplier
Approved Laboratory of International Wool Secretariat

Members of:
American National Standards Institute
American Society for Testing and Materials
British Standards Institute

Hong Kong Association of Certification Laboratories
Hong Kong Toys Council

TEST REPORT

NUMBER: TJ00004407

TESTS CONDUCTED (AS REQUESTED BY THE APPLICANT)

- 1 APPEARANCE AFTER WASH (12 MINUTES MACHINE WASH AT 105°F, NORMAL CYCLE, IN AATCC 1993 DETERGENT SOLUTION, FOLLOWED BY TUMBLE DRY - COTTON/STURDY):

AFTER THE 1ST WASH

OBSERVATION :

- . NO MATTING OR BUNCHING UP OF PADDING WAS FOUND.
 - . THE WASHED SAMPLE FADED SLIGHTLY.
 - . A FEW PADDING FIBRES WERE FOUND PENETRATING THROUGH THE WOVEN AND ITS STITCHINGS.
 - . TINY CREASES WERE FOUND ON WOVEN.
 - . MODERATE PUCKERS WERE FOUND ALONG THE STITCHINGS.
- THE GENERAL APPEARANCE OF THE WASHED SAMPLE WAS STILL ACCEPTABLE.

AFTER THE 2ND WASH

OBSERVATION :

- . NO MATTING OR BUNCHING UP OF PADDING WAS FOUND.
 - . THE WASHED SAMPLE FADED SLIGHTLY.
 - . A FEW PADDING FIBRES WERE FOUND PENETRATING THROUGH THE WOVEN AND ITS STITCHINGS.
 - . TINY CREASES WERE FOUND ON WOVEN.
 - . MODERATE PUCKERS WERE FOUND ALONG THE STITCHINGS.
- THE GENERAL APPEARANCE OF THE WASHED SAMPLE WAS STILL ACCEPTABLE.

AFTER THE 3RD WASH

OBSERVATION :

- . NO MATTING OR BUNCHING UP OF PADDING WAS FOUND.
 - . THE WASHED SAMPLE FADED SLIGHTLY.
 - . A FEW PADDING FIBRES WERE FOUND PENETRATING THROUGH THE WOVEN AND ITS STITCHINGS.
 - . TINY CREASES WERE FOUND ON WOVEN.
 - . MODERATE PUCKERS WERE FOUND ALONG THE STITCHINGS.
- THE GENERAL APPEARANCE OF THE WASHED SAMPLE WAS STILL ACCEPTABLE.